

SNOW RABBIT C2S CFS / COATED ART PAPER, GLOSS

Basis weight	Peso Base	LBS	71	81	86
Basis weight	Peso Base	g/m ²	105	120	128
Brightness	Blancura	%	90±1	90±1	90±1
CIE Brightness	CIE Blancura	%			
Caliper	Calibre	µm	86±2	97±2	106±2
Bulk	Volumen	cm ³ /g	0.82	0.81	0.83
IGT	IGT	m/s	≥1.8	≥1.8	≥1.8
Smoothness	Suavidad	S	≥1000	≥1000	≥1000
Gloss	Brillo	%	60±2	60±2	60±2
Roughness	Rugosidad	µm	≤1.3	≤1.3	≤1.3
Ink Absorption	Absorción de tinta	%	16-20	16-20	16-20
Humidity	Humedad	%RH	40-43	40-43	40-43

Test condition: ISO Temperature: 23±1⁰C Humidity: 50±2%RH

SNOW RABBIT C1S CFS / Coated Art Paper

Basis weight	Peso Base	LBS	54	61	68
Basis weight	Peso Base	g/m ²	80	90	100
Brightness	Blancura	%	91±1	91±1	91±1
CIE Brightness	CIE Blancura	%	105±2	105±2	105±2
Caliper	Calibre	µm	62±2	71±2	80±2
Bulk	Volumen	cm ³ /g	1	1	1
IGT	IGT	m/s	≥1.6	≥1.6	≥1.7
Smoothness	Suavidad	S	≥1000	≥1000	≥1000
Gloss	Brillo	%	58±2	58±2	58±2
Roughness	Rugosidad	µm	≤1.2	≤1.2	≤1.2
Ink Absorption	Absorción de tinta	%	16-21	16-21	16-21
Humidity	Humedad	%RH	40-43	40-43	40-43

Test condition: ISO Temperature: 23±1⁰C Humidity: 50±2%RH

101	106	135
150	157	200
90±1	90±1	90±1
126±2	134±2	174±2
0.84	0.85	0.87
≥1.8	≥1.8	≥1.8
≥1000	≥1000	≥1000
60±2	60±2	60±2
≤1.3	≤1.3	≤1.3
16-20	16-20	16-20
40-43	40-43	40-43

81
120
91±1
105±2
97±2
1
≥1.7
≥1000
58±2
≤1.2
16-21
40-43