

**SNOW RABBIT C2S CFS / COATED ART PAPER, GLOSS**

Basis weight	Peso Base	LBS	71	81	86	101	106	135
Basis weight	Peso Base	g/m <sup>2</sup>	105	120	128	150	157	200
Brightness	Blancura	%	90±1	90±1	90±1	90±1	90±1	90±1
CIE Brightness	CIE Blancura	%						
Caliper	Calibre	µm	86±2	97±2	106±2	126±2	134±2	174±2
Bulk	Volumen	cm <sup>3</sup> /g	0,82	0,81	0,83	0,84	0,85	0,87
IGT	IGT	m/s	≥1.8	≥1.8	≥1.8	≥1.8	≥1.8	≥1.8
Smoothness	Suavidad	S	≥1000	≥1000	≥1000	≥1000	≥1000	≥1000
Gloss	Brillo	%	60±2	60±2	60±2	60±2	60±2	60±2
Roughness	Rugosidad	µm	≤1.3	≤1.3	≤1.3	≤1.3	≤1.3	≤1.3
Ink Absorption	Absorción de tinta	%	16-20	16-20	16-20	16-20	16-20	16-20
Humidity	Humedad	%RH	40-43	40-43	40-43	40-43	40-43	40-43

Test condition: ISO Temperature: 23±1<sup>0</sup>C      Humidity: 50±2%RH

**SNOW RABBIT C1S CFS / Coated Art Paper**

Basis weight	Peso Base	LBS	54	61	68	81
Basis weight	Peso Base	g/m <sup>2</sup>	80	90	100	120
Brightness	Blancura	%	91±1	91±1	91±1	91±1
CIE Brightness	CIE Blancura	%	105±2	105±2	105±2	105±2
Caliper	Calibre	µm	62±2	71±2	80±2	97±2
Bulk	Volumen	cm <sup>3</sup> /g	1	1	1	1
IGT	IGT	m/s	≥1.6	≥1.6	≥1.7	≥1.7
Smoothness	Suavidad	S	≥1000	≥1000	≥1000	≥1000
Gloss	Brillo	%	58±2	58±2	58±2	58±2
Roughness	Rugosidad	µm	≤1.2	≤1.2	≤1.2	≤1.2
Ink Absorption	Absorción de tinta	%	16-21	16-21	16-21	16-21
Humidity	Humedad	%RH	40-43	40-43	40-43	40-43

Test condition: ISO Temperature: 23±1<sup>0</sup>C      Humidity: 50±2%RH